## **Amendments to the Claims:**

This listing will replace all prior versions, and listing, of claims in the application:

## **Listing of Claims:**

- 1. (Currently Amended) An ink jet recording element comprising a support having thereon an image-receiving layer comprising a polymeric binder in an amount of from about 5 to about 30% by weight and non-silicon-containing inorganic oxidealumina particles, in an amount of from about 40 to about 95% by weight, said particles being pseudo-boehmite, alumina, zirconia, titania, yttria or ceria-and having their surfaces treated with a silane coupling agent, having a hydrophilic, organic moiety, in an amount of from about 0.01 to about 0.5 mmol/gram.
  - 2. Canceled.
  - 3. Canceled.
  - 4. Canceled.
- 5. (Original) The recording element of Claim 1 wherein said silane coupling agent is N-(trimethoxysilylethyl)benzyl-N,N,N-trimethylammonium chloride; N-trimethoxysilylpropyl-N,N,N-tributylammonium chloride; octadecyldimethyl(3-trimethoxysilylpropyl)ammonium chloride; or N-(3-triethoxysilylpropyl)-4,5-dihydroimidazole.
  - 6. Canceled.
- 7. (Previously Presented) The recording element of Claim 1 wherein said polymeric binder is poly(vinyl alcohol).
  - 8. Canceled.
- 9. (Original) The recording element of Claim 1 wherein said imagereceiving layer is present at a thickness of from about 1 μm to about 60 μm.

- 10. (Currently Amended) The recording element of Claim 1 wherein said <u>alumina inorganie oxide</u>-particles have a particle size of from about 5 nm to about 1,000 nm.
- 11. (Original) The recording element of Claim 1 wherein a base layer is present in between said support and said image-receiving layer.
- 12. (Original) The recording element of Claim 11 wherein said base layer comprises inorganic particles and a polymeric binder.
- 13. (Original) The recording element of Claim 12 wherein said inorganic particles are calcium carbonate, calcined clay, aluminosilicates, zeolites or barium sulfate.
- 14. (Original) The recording element of Claim 12 wherein said polymeric binder is a styrene/acrylic latex, styrene/butadiene latex or poly(vinyl alcohol).